


MOUNTAINEERING EQUIPMENT (16 ITEMS)

103. GLOVES LEATHER WHITE LINED

FIRST REVISION: IS 5866-1979

	Qualitative Requirements	Picture of Equipment
GENERAL	For Manufacture Of This ;Eather Preserved Sheep,Goat Or Calf Skins Free Frome Adverse Grain Defets, Cuts And Holes Shall Be Used.	
MATERIAL	The lather shall be chrome tanned in either natural finish or with white pigment finish and shall be shoft and pliable uniform colour even thickness smooth feel and compact texture, free from fly cuts, grain defects like pock marks, tick marks, cuts pin holes scratches, perforation, store marks, vulture marks ,abrasions etc.	
FINISH	Natural colour finish	
WATERPROF NESS	No material which known to be toxic or harm full to the skin and which may cause dermatitis, chafing or irritation shall be used for waterproofing white pigment finish with suitable blinder .	
Physical Requirement	Thickness range : 0.7 to 1.0 mm Tensile strength : MPa, Min 15 Double hole stitch tear strength, KN/m Thickness , Min :44 Crankiness of the gain: the grain shall not crack at the double fold when leather is folded with the grain side. Water vapour permeability/m2/h : 20	
Packing and Marking	As agreed to purchaser and supplier	
Marking	Each skin shall clearly and legibly be markedat one corner on the flesh of skin with trade mark ,if any size, month and year of manufacture .	
Length & Width	As Per IS : 5914-1970	